

MM820 2 part moulding compound

Description

This is a two-component low tear room temperature condensation cure silicone system. The cured rubber is suitable for the mould making of patterns with fine details, where some dimensional stability is required. Low tear silicone moulding rubbers are cost effective for the production of moulds only requiring a few impressions. They find uses in the reproduction of plane surface objects

Key Features

- Easy demoulding
- Easily degassed
- Low viscosity
- Fine detail pick up

Application

reproduction of plane surface models

Use and Cure Information

The curing process starts as soon as the catalyst is added. Under normal conditions of temperature and humidity typical curing characteristics are described below. If the product is to be used in contact with aggressive chemicals, such as high styrene polyester resins or epoxies, it is recommended that the rubber be allowed to cure for 48 hours before use.

Pour the catalysed rubber into the mould from one point, ensuring air is not entrapped. Allow the rubber to cure before removing from the mould. To allow the rubber to achieve its maximum physical properties and chemical resistance leave the partially cured rubber to age at room temperature for at least a further 12 hours.

How to Use

Charge the base rubber into a clean plastic or metal container, approximately 3-4 times its volume.

Add standard catalyst in the proportion of 5 parts by weight of catalyst to 100 parts by weight of the rubber base. Mix thoroughly, slowly at first to avoid splashing and taking care to avoid excessive air entrapment. After catalysation any entrapped air may be removed by intermittent evacuation for several minutes. The use of a sufficiently large container permits degassing without overflow.

Catalysts

Use the following catalysts:

Code	Colour	Pot Life	De-Mould
MM CAT L5 NT	Clear	>60 mins	<24 hrs

Health & Safety

Health and Safety

Safety Data Sheets available on request.

Packaging

CHT Moulding Rubbers are available in a variety packaging including bulk containers. Please contact our sales department for more information.

Revision Date 12 Feb 2024
Revision No 2
Download Date 18 May 2024

Property

Uncured Product

Cure Profile		23°C and 50% humidity
Cure Type		Condensation
De-mould Time / Full Cure at 23°C/73°F		2 hr hrs
Mix Ratio By Weight		20:1
Pot Life mins at 23°C/73°F		15 min mins
Rheology		Liquid
Viscosity Mixed	Brookfield	4800 cP

Cured Product

7 days at 23+/-2°C and 50+/-5% humidity		
Color		Gray
Density	BS ISO 2781	1.25 g/cm3
Elongation at Break	ISO 37	150 %
Hardness Shore A	ASTM D 2240-95	20
Linear Shrinkage (%)		0.5 %
Max Working Temp		180 °C / 356 °F
Min Working Temp		-50 °C / -58 °F
Tear Resistance (N/mm)	BS ISO 34-1	2.45 N/mm / 14 ppi
Tensile Strength	ISO 37	1.76 N/mm2 / 255 psi

Storage

Max Storage Temperature	40 °C / 104 °F
Shelf Life	12 mths